

新加坡PSB实验室检测
抗菌率达到99%以上

TEST REPORT

Your Ref:

Date: 17 Dec 2004



RESULTS

Product : "Megastar Bioshield" Anti- Microbial Coating

Test microorganism (Bacterial cell concentration)	Count of test microorganism recovered from the inoculated sample	Percentage Reduction
<i>Staphylococcus aureus</i> ATCC 6538 (6.4 x 10 ⁵ cfu/ml)		
0 hour	580 000	-
24 hours	Less than 100	> 99.98
<i>Klebsiella pneumoniae</i> ATCC 4352 (7.1 x 10 ⁵ cfu/ml)		
0 hour	920 000	-
24 hours	Less than 100	> 99.99
<i>Escherichia coli</i> ATCC 10536 (4.9 x 10 ⁵ cfu/ml)		
0 hour	1 200 000	-
24 hours	Less than 100	> 99.99
<i>Aspergillus niger</i> ATCC 6275 (2.3 x 10 ⁵ cfu/ml)		
0 hour	320 000	-
24 hours	Less than 100	> 99.97

CHENG-SHAW LAY ENG (MRS)
TECHNICAL EXECUTIVE

KAM-LEONG YIN PHENG (MRS)
MICROBIOLOGIST
MICROBIOLOGY
TESTING GROUP

